## DATASHEET

## **ASTM Property**





Grade	VC590
Product	EVA

General Information			
Key Features	VC590 is manufactured by high pressure autoclave process and designed for base resin of variety of wire & cable compounds such as semi-conductive compound, flame retardant compound.  VC590 is well known for its excellent processability, filler loadability and high quality assurance.		
Applications	Excellent Foam Molding Property  Very Good Mechanical Properties  Excellent Loading Property of Various Fillers		

ltem	Measuring Method	Unit	Value		
Physical					
Melt Flow Index	ASTM D1238	g/10min	4.0		
Density	ASTM D1505	g/cm³	0.952		
Vinyl Acetate Content	LC Method	%	28		
Mechanical					
Tensile Stress (Yield)	ASTM D638	kgf/cm²	200		
Tensile Strain (Break)	ASTM D638	%	800		
Thermal					
Melting Point	LC Method	$^{\circ}$	72		
VICAT Softening Temperature	ASTM D1525	$^{\circ}$	47		
Additional Properties					
Hardness (Shore D)	ASTM D2240	D scale	30		

1. Physical Properties: these are not to be construed as specifications

2. ISO 9001, 14001, /TS 16949

\* The last update date : 2021/10/01