

M7100

High-density polyethylene (HDPE)



Description

M7100 is a high-density polyethylene resin produced by Mitsui(Slurry) Process, suitable for Pipe Extrusion which has high hydrostatic pressure resistance and ESCR having excellent formability.

Characteristics

- For Pipe Extrusion Molding
- ISO PE100 (MRS 10) Class
- Good processability, Good mechanical properties

Applications

- Water supply pipes, Sewerage pipe, Gas pipe, etc.

Properties

	Properties	Test Method		Values	Nominal
Physical	Melt Flow Index (190°C, 2.16/5kg)	ASTM	D1238	0.06/0.25	g/10min
	Density	ASTM	D1505	0.952	g/cm ³
Mechanical	Tensile Stress (Yield)	ASTM	D638	230	kgf/cm ²
	Tensile Strain (Break)	ASTM	D638	> 700	%
	Flexural Modulus	ASTM	D790	8,500	kgf/cm ²
	Notched IZOD Impact Strength (23°C)	ASTM	D256	NB	kgf-cm/cm
	Rockwell Hardness	ASTM	D785	57	R
	ESCR	ASTM	D1693	> 1,000	F50hr
Thermal	VICAT Softening Point	ASTM	D1525	125	°C
	Oxidative Induction Time (200°C)	ISO/TR	10837	> 30	min
Hydrostatic pressure	12.4MPa (20°C)	ISO	1167	> 100	hr
	5.4MPa (80°C)	ISO	1167	> 165	hr
	5.0MPa (80°C)	ISO	1167	> 1,000	hr

• NOTE : these are not to be construed as specifications

*DISCLAIMER : THIS DOCUMENT (INCLUDING ANY ENCLOSURES AND ATTACHEMENTS) HAS BEEN PREPARED FOR THE EXCLUSIVE USE AND BENEFIT OF THE ADDRESSEE(S) AND SOLELY FOR THE PURPOSE FOR WHICH IT IS PROVIDED. LOTTE CHEMICAL MAKES NO WARRANTY OR REPRESENTATION WHATSOEVER, EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE WITH RESPECT TO THIS DOCUMENT OR ANY INFORMATION HEREIN; AND LOTTE CHEMICAL ASSUMES NO LIABILITY WHATSOEVER WITHOUT LIMITATION WITH RESPECT TO ANY DAMAGES INCLUDING, BUT NOT LIMITED TO, DIRECT, INDIRECT, SPECIAL, CONSEQUENTIAL, OR PUNITIVE DAMAGES ARISING OUT OF, RESULTING FROM, OR ANY WAY CONNECTED TO ANY USE OF THIS DOCUMENT OR ANY INFORMATION HEREIN.

